


carrière : Chateau-Gaillard	client : Controle Interne
Granulats : Gravier Sableux 0/20	
Pétrographie : Silico-Calcaire	
Elaboration : Roulé Lavé	
Usage : Bétons hydrauliques	

Résultats de production

du 06/06/04 au 19/02/07

	0.063	0.125	0.25	0.5	1	2	4	6.3	8	10	12.5	14	16	20	22.4	28	40
Moyenne Xf	0.69	2.13	9.03	26.14	35.63	42.90	54.06	61.75	66.21	72.09	79.44	85.59	92.03	98.31	99.49	100.00	100.00



WIL 8.0.1 (c) Arcade 1996,2006

TROUILLOT